e-nedzi.com

SPA-F

Plastic Screw RENY / Phillips Cross Recessed Flat Head Machine Screws





Material/Finish

🦸 RoHS

	SPA-F
Main body	RENY*1 (50% Glass Fiber Reinforced Polyamide MXD6) (Ivory)
Heat Resistance Temperature* ²	105℃

- *1: RENY is a registered trademark of Mitsubishi Engineering-Plastics Corporation.
- *2: This is the value for the plastic material. The maximum operating temperature of the product changes with performance conditions such as tightening torque.



- RENY is a thermoplastic super-engineering plastic with excellent tensile and flexural strength.
- Screws have excellent fatigue resistance, creep resistance, and thermal insulation.
- While it is nearly as strong as metal, its weight is approximately 1/5 of iron.
- The properties and precautions of plastic screws

 → P.xxxx

Application

Electrical and electronic equipment / Insulation and dew condensation prevention for refrigerators and freezers / Aquatic applications / Electrochemical plating / Lightweight applications in automobiles, aircrafts, and spacecrafts

																				Unit : mm
	M (Coarse)			L 🕢												Tension*1	Torsional*1			
Part Number	Nominal of Thread 1	Pitch											D1	Lı		LOAD	Torque (N∙m)	Mass	(g)	Qty per pack
SPA-M2-F	M2	0.4			6	8	10						4	1.2	1	350	0.101	0.038	- 0.053	50
SPA-M2.6-F	M2.6	0.45	4		6	8	10	12					5.2	1.5	1	611	0.22	0.043	- 0.094	50
SPA-M3-F	M3	0.5		5	6	8	10	12	15	20	25		6	1.75	2	853	0.36	0.1	- 0.25	50
SPA-M4-F	M4	0.7			6	8	10	12	15	20	25		8	2.3	2	1499	0.85	0.22	- 0.52	50
SPA-M5-F	M5	0.8					10	12	15	20	25		10	2.8	2	2407	1.65	0.52	- 0.86	20
SPA-M6-F	M6	1					10	12	15	20	25	30	12	3.4	3	3106	2.74	0.83	- 1.6	20
SPA-M8-F	M8	1.25							15	20	25	30	16	4.4	3	5335	6.22	2.1	- 3.1	10

*1: Values in chart are for reference only. They are not guaranteed values. The recommendation torque is 50% of the torsional torque.

• When purchasing less volume than one full bag, a separate handling fee is charged. For details, see the Sold Separately Service.

• Part number specification



 Individual Sales → P.xxxx
 Scientification process for captive use → P.xxxx

 Available / Add'l charge
 Available

 Not Available
 Not Available

