e-nedzi.com

SPA-LC Plastic screw - Hex Socket Low Head Bolt - RENY

RoHS

TProtrusion 💾 High strength



• Material/Finish

	SPA-LC
Main body	RENY*1 (Glass Fiber 50% Reinforced Polyamide MXD6) (Black)
Heat resistance temperature* ²	105℃

- *1: RENY is a registered trademark of Mitsubishi Engineering-Plastics Corporation.
- *2: A value of plastic materials. The allowable operating temperature of the product varies depending on use conditions such as tightening torque.



- Hex socket head cap screw with low head.
- For space-saving of equipment/device and applications with a limited top space.
- RENY is thermoplastic engineering plastics with excellent tensile strength and bending strength.
- It is highly fatigue-resistant and has excellent creeping and heat insulation properties.
- While it is nearly as strong as metal, its weight is approximately 1/5 of iron.
- The properties and precautions of plastic screws
 P.xxxx

Application

Heat insulation and dew condensation prevention of electric and electronic devices / refrigerating and freezing facilities / Weight saving of offshore instruments, plating facility and automobile, aircraft and space equipment, etc.

Part Number	M (Coarse)														Tension*1 Rupture	Torsional*1		Qty
	Nominal of Thread 1	Pitch	L 4 2							D1	L1	В	Load (N)	Torque (N∙m)	Mass (g)	per pack		
SPA-M3-LC	M3	0.5	6	8	10	12	16	20				5.5	2	2	799	0.2	0.11 - 0.25	20
SPA-M4-LC	M4	0.7	6	8	10	12	16	20	25			7	2.8	2.5	1286	0.74	0.24 - 0.58	20
SPA-M5-LC	M5	0.8	6	8	10	12	16	20	25	30		8.5	3.5	3	1976	1.08	0.39 - 1	20
SPA-M6-LC	M6	1			10	12	16	20	25	30	40	10	4	4	2767	2.26	0.75 - 2.1	20

*1: Values in chart are for reference only. They are not guaranteed values. The recommendation torque is 50% of the torsional torque.

• When purchasing less volume than one full bag, a separate handling fee is charged. For details, see the Sold Separately Service.

• Part number specification



 Individual Sales → Pxxxxx
 S Cleanroom Wash & Packaging → Pxxxx
 Image: Second Sec

