## **SNCW**


## Slotted Cheese Head Machine Screws (Pure Tungsten)











## Material/Finish



	SNCW
Main Body	Pure Tungsten(99.99 % or above)

## • Physical Properties

	Pure Tungsten	SUS304
Specific Gravity	19.3	7.93
Specific Heat (J/kg·K)	138	500
Electric Resistance ( $\mu\Omega$ · m)	0.054	0.7
Thermal Conductivity (W/( $m \cdot K$ ))	174	17
Linear Expansion Coefficient (K <sup>-1</sup> )	4.36 × 10 <sup>-6</sup>	17.3 × 10 <sup>-6</sup>

• Values in chart are for reference only. They are not guaranteed values.



- Made of tungsten, with characteristics including a high melting point, high specific gravity and high purity.
- Melting point: 3683℃
- The specific gravity is at least twice that of general steel and stainless steel.
- Excellent chemical resistance also includes resistance to hydrofluoric acid.
- Cleanroom wash/cleanroom packing provided.
- Application

FPD production equipment / Semiconductor manufacturing equipment / Printed circuit board etching devices /

Metallic surface treatment equipment and facilities / Chemical plants

Unit	٠	mm

Part Number 1	M (Coarse)	L 12							D1	L1	а		Tensile Breaking Load *1	Mass (g)	
	Nominal of Thread	Pitch							Di	LI	а		(N)	iviass (g)	
SNCW-M3	M3	0.5	6	8	10					5.5	2	0.8	0.85	1500	1.6 - 2.1
SNCW-M4	M4	0.7		8	10	12				7	2.6	1.2	1.1	2600	3.6 - 4.5
SNCW-M5	M5	0.8			10	12	16	20		8.5	3.3	1.2	1.3	4200	7 - 10.7
SNCW-M6	M6	1				12	16	20	25	10	3.9	1.6	1.6	6000	11.8 - 18.7

\*1: Values in chart are for reference only. They are not guaranteed values.

• Part Number Specification



Batch cleanroom packing is provided for orders containing multiple items of the same size.





