SHNT Hex Nuts - Titanium

🕵 Cleanroom wash & packaging 🖕 Chemical-proof 🏾 🏹 Non-Magnetic 🥖 Lightweight

SHNT





SHNT-F т

tı.

M

Physical property

M

	TW270 (Grade 1 Titanium)	TW340 (Grade 2 Titanium)		
Specific Gravity	4.51	4.51		
Melting Point (℃)	1668	1668 106 17.16		
Longitudinal Elastic Modulus (GPa)	106			
Thermal Conductivity (W/(m·K))	17.16			
Linear Expansion Coefficient (K-1)	8.4×10 ⁻⁶	8.4×10 ⁻⁶		
Electric Resistance ($\mu \Omega \cdot m$)	0.55	0.55		
Amplitude Permeability (μ)	1.0001 (Nonmagnetic)	1.0001 (Nonmagnetic)		

• Values in chart are for reference only. They are not guaranteed values.

Mechanical property

	TW270 (Grade 1 Titanium)	TW340 (Grade 2 Titanium)		
Tensile Strength (N/mm ²)	270 - 410	340 - 510		
0.2% Proof Stress (N/mm ²)	165 or Higher	215 or Higher		
Elongation (%)	27 or Higher	23 or Higher		

• Values in chart are for reference only. They are not guaranteed values.



- Specific gravity is approximately 60% of stainless steel.
- Nonmagnetic.
- Excellent chemical and seawater resistance.
- Chemical polishing and brightening processing improve the screw surface. Furthermore, the screws are cleanroom washed, cleanroom packed, and comply with clean specifications that require no oil or foreign matter deposits.
- Application

Lightweight applications in automobiles, aircrafts, spacecrafts, and robots FPD production equipment, semiconductor devices, electrical and electronic equipment, aquatic applications, and electrochemical plating

• Material/Finish Ø ROH				
		SHNT	SHNT-F	
	Main body	TW270 (Grade 1 Titanium)	TW340 (Grade 2 Titanium)	

• Part number specification

SHNT-M6-F 11

Batch cleanroom packing is provided for orders containing multiple items of the same size.

SHNT Hex Nuts - Titanium	Unit:mm					
Part Number 📶	M (Coarse)		в	т	Mass (g)	
	Nominal of Thread	Pitch	D	1	Mass (g)	
SHNT-M3	М3	0.5	5.5	2.4	0.2	
SHNT-M4	M4	0.7	7	3.2	0.46	
SHNT-M5	M5	0.8	8	4	0.69	
SHNT-M6	M6	1	10	5	1.4	
SHNT-M8	M8	1.25	13	6.5	3.1	
SHNT-M10	M10	1.5	17	8	6.5	

SHNT-E Hex Flange Nuts - Titanium

						Unit : mm
M (Coarse)		Р	т	+.	D	Mass (g)
Nominal of Thread	Pitch	Б	1	u	D	Mass (g)
M3	0.5	5.5	3.7	0.8	8	0.4
M4	0.7	7	4.2	0.8	10	0.72
M5	0.8	8	5.5	1.1	12	1.3
M6	1	10	6	1.5	14	1.9
M8	1.25	12	7.5	1.5	17	3.3
M10	1.5	14	9	1.8	19	4.8
	M (Coarse) Nominal of Thread M3 M4 M5 M6 M8	M (Coarse)Nominal of ThreadPitchM30.5M40.7M50.8M61M81.25	M (Coarse) Pitch Nominal of Thread Pitch M3 0.5 M4 0.7 M5 0.8 M6 1 M8 1.25	M (Coarse) Pitch P Nominal of Thread Pitch 3.7 M3 0.5 5.5 3.7 M4 0.7 7 4.2 M5 0.8 8 5.5 M6 1 10 6 M8 1.25 12 7.5	M (Coarse) Pitch T 1 M3 0.5 5.5 3.7 0.8 M4 0.7 7 4.2 0.8 M5 0.8 8 5.5 1.1 M6 1 10 6 1.5 M8 1.25 12 7.5 1.5	M (Coarse) Pitch T th D M3 0.5 5.5 3.7 0.8 8 M4 0.7 7 4.2 0.8 10 M5 0.8 8 5.5 1.1 12 M6 1 10 6 1.5 14

1 Individual Sales 1 piece in 1 pack

Cleanroom washed and packed Not Available

📢 Cleanroom Wash & Packaging 📲 Screw Length Adjustment 💶 Vibration Resistant 🛛 Not Available

Modification process for captive use Not Available

NBK